


WDS[®] Nextra and Nextra HY Panel

Product Data Sheet



Product Description

WDS Nextra Panel is a rigid compact microporous insulation constituted of a mineral core enveloped in a non-combustible cloth being typically E Glass.

Its engineered mineral matrix is designed for applications where the lowest thermal conductivity up to 1000°C (1832°F) is the main selection criteria.

Like any other microporous insulation of our industrial range produced with our exclusive WDS Technology process, it features extremely good handling properties, low thermal conductivity coefficient giving it very good insulating properties in limited thickness allowing to design equipment where high energy efficiency, space optimization and reduction of weight are premium factors to be considered.

Features

- Best-in-class amongst other market solutions within the same classification temperature and similar chemistry, for the lowest thermal conductivity it provides in the entire temperature spectrum up to its classification temperature.
- Not affected by thermal shock
- Good resistance to compression associated to its low density
- Excellent cutting properties

Benefits

- Dimensionally stable over time up to the maximum using temperature
- Helps to control energy efficiency and heat flow very precisely
- Easy to cut and with proven installation techniques.
- Freedom in engineering at the design stage
- Increases effective volume inner capacity or reduces encumbrance in equipment and apparatus of any kind.
- Environmentally friendly

Applications

- Metal production
- Petrochemical process units
- Energy storage
- Fuel Cells
- Glass making
- Ceramic kilns
- Cement kilns
- Power Generation
- Incineration

Environmental and Health Safety

WDS Nextra Panel does not contain any hazardous or decomposition substance according to the EU Directive 2006/1907/EEC and IARC. The fibers or filaments used as reinforcement of the mineral core are also exonerated from any classification as defined by the WHO (World Health Organization) and EU Directive 97/69/EC.

Resistance to Moisture and Water

WDS Nextra Panel can also be supplied in a hydrophobic version which is water repellent in its entire thickness; the water repellent treatment withstands up to 250°C (482°F) continuously. Non condensed moisture does not affect the product.

WDS[®] Nextra and Nextra HY Panel

Product Data Sheet



Properties	WDS Nextra Panel	WDS Nextra HY Panel
Classification Temperature, °C (°F)	1000 (1832)	1000 (1832)
Density, kg/m ³ (pcf), nominal	275 (17.2)	275 (17.2)
Cold Compression Strength, MPa (psi), ASTM C 165	> 0.25 (31.9)	> 0.25 (31.9)
Linear Shrinkage, %, ASTM C 365		
Full soak, 1000°C (1832°F), 24 hours	<3.0	<3.0
Chemical Analysis, %		
Silica, SiO ₂	55-75	
Silicon Carbide, SiC	25-40	
Others	3-10	
Loss of Ignition, Dry condition	<2.5	
Thermal Conductivity, W/m·K (BTU·in/hr·ft²·°F), ASTM C 177		
200°C (392°F)	0.024 (0.167)	
400°C (752°F)	0.026 (0.180)	
600°C (1112°F)	0.030 (0.208)	
800°C (1472°F)	0.035 (0.243)	

Shelf Life

- The product has unlimited shelf life when properly stored in dry conditions; moisture does not affect the products however condensation should be avoided for the hydrophilic version.

Standard Dimensions and Availability

Dimensions, mm (in)	Thickness, mm (in)
1000 x 1000 (39.3 x 39.3)	10, 12, 15, 17, 20, 25, 30, 35, 40, 45, 50 (0.4, 0.5, 0.6, 0.7, 0.8, 1, 1.18, 1.37, 1.57, 1.77, 2)
1000 x 650 (39.3 x 23.6)	
915 x 610 (47.24 x 39.27)	

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.