

Superwool[®] Bults



Datasheet Code US: 1114-100

© 2013 Thermal Ceramics is a business of Morgan Advanced Materials



Product Features

- Low Bio-Persistence
- Excellent Insulating Performance
- Excellent Thermal Shock Resistance
- Low Heat Storage Capacity
- Different Compositions, Grades and Forms to Meet a Variety of Needs

Product Description

Superwool is manufactured from pure raw materials and processed to offer excellent performance in high-temperature applications. Superwool offers an alternative to traditional solutions due to its high refractoriness and excellent non-wetting characteristics with molten aluminum.

Superwool provides stability and resistance to chemical attack. Exceptions include hydrofluoric acid, phosphoric acid and strong alkalies (i.e. NaOH, KOH). Superwool is unaffected by incidental spills of oil or water. Thermal and physical properties are restored after drying.

Superwool is ideally suited to individual applications and is available in a wide range of thicknesses and densities. The maximum continuous use temperature depends on the application. Refer to your local Thermal Ceramics representative for advice.

Applications

- Expansion Joints
- Low Mass Kiln Cars
- Tube Seal Fabrication
- Thermal and Acoustical Insulation
- Filtration Media
- Reinforcement and Filler for Plastics, Resins and Paints
- Fillers for Mastics, Cements and Vacuum Formed Boards and Shapes

Type

Alkaline Earth Silicate (AES) Wool
CAS number: 329211-92-9

Superwool[®] Bulks



	Superwool Plus	Superwool HT
Color	white	white
Continuous Use Temp, °F (°C)	1832 (1000)	2102 (1150)
Classification Temp, °F (°C)	2192 (1200)	2372 (1300)
Average Specific Heat	0.26 BTU/lb-°F @ 1800°F (1.08 kJ/kg-°C @ 982°C)	
Fiber Length, in (mm)	½ - 10 (13-250)	

Chemical Analysis, %, Weight Basis After Firing

Silica, SiO ₂	62 - 68	70 - 80
Lime + Magnesia, CaO + MgO	29 - 39	18 - 25
Other	<1	<3
Leachable Chlorides	trace	-

Availability and Packaging

Thermal Ceramics Bulk fibers are packaged in either cartons or bags and stretch-wrapped onto pallets. Standard Packaging on Lubricated Bulk Fibers is 25 lb cartons. Standard Packaging on Un-Lubricated Bulk Fibers is 40 or 50 lb bags. Please check with your Thermal Ceramics office for current lead times and availability.

	Grade	Typical Fiber Index	Fiber Length	Lubrication
Superwool Plus, Superwool HT	111	45-70%	up to 10 in (250mm)	Yes
	112	45-70%	up to 10 in (250mm)	No
	HM-12	50-70%	½ in (13mm)	No
	HM-25	50-70%	1 in (25mm)	No
	HM-50	50-70%	2 in (50mm)	No
Engineered Fibers	Various	60-90%	Various	No

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Thermal Ceramics office to obtain current information. This product may be covered by one or more patents or foreign equivalents: A list of patent numbers is available upon request to Morgan Advanced Materials. Thermal Ceramics, Superwool, Plus and HT are trademarks of Morgan Advanced Materials plc.