



# WDS<sup>®</sup> NextraShell<sup>™</sup>

## Product Data Sheet

### Product Description

WDS NextraShell is a mechanically robust 3D microporous insulation formed into curved segments and shells of various diameters and thicknesses.

The engineered mineral matrix has been specifically designed for applications where mechanical resistance, associated with very light weight, are a key selecting criteria.

Like any other microporous insulation of our industrial range produced with our exclusive WDS Technology process, it features extremely good handling properties, extremely low thermal conductivity coefficient giving it very good insulating properties in limited thickness, allowing to design equipment where high energy efficiency, space optimization and reduction of weight are other premium factors to be considered.

### Features

- Very high compactness
- Very low thermal conductivity
- Not affected by thermal shock
- Improved product mineral matrix core features minimal dust release and very good handling and machining abilities
- Good resistance to compression
- Homogeneity throughout the entire surface and thickness of the board
- Highly efficient insulation in limited space and weight constraints
- Inorganic and non-combustible
- Unaffected by most chemicals
- Structural integrity

### Benefits

- Dimensionally stable over time
- Pedestrian resistance once installed
- Easy to cut and with proven installation techniques
- Very low weight lining system can be foreseen due to the extremely favorable product density / thickness ratio
- Environmentally friendly
- Helps to control energy efficiency and heat flow very precisely
- Increases effective volume inner capacity or reduces encumbrance

### Applications

- Ultra-thin insulation for pipe racks

### Application Advantages

- Less quantity of metal cladding required
- Perfect fit for fast installation and efficiency pipe sealing
- Very good pedestrian resistance once installed.
- Water resistant encapsulation available
- Perfect combination with our water repellent Superwool<sup>®</sup> blankets to address corrosion under insulation at best

### Environmental and Health Safety

WDS NextraShell does not contain any hazardous or decomposition substance according to the EU Directive 2006/1907/EEC and IARC. The fibers or filaments used as reinforcement of the mineral core are also exonerated from any classification as define by the WHO (World Health Organization).

### Resistance to Moisture and Water

WDS NextraShell has a non-porous surface therefore it is sensitive to all liquids that can wet it; this includes substances such as water, oil and petroleum spirit, since they can destroy the pore structure. Non condensed moisture does not affect the product.

Sensitivity to liquids of WDS NextraShell can be eliminated by using a surface treatment such as temperature resistant aluminum foil or shrink wrapping with PE Film.

Physical Properties		WDS NextraShell
Classification Temperature, °C (°F)		1000 (1832)
Density, kg/m <sup>3</sup> (pcf), nominal		275 (17.2)
Cold Compression Strength, MPa (psi), ASTM C 165		>0.3 (>43.5)
Linear Shrinkage, %, ASTM C 365		
	Full soak, 1000°C (1832°F), 24 hours	<3.0
Chemical Analysis, %		
	Silica, SiO <sub>2</sub>	75-85
	Silicon Carbide, SiC	12-20
	Others	3-10
	Loss of Ignition, Dry condition	<1.5
Thermal Conductivity, W/m·K (BTU·in/hr·ft <sup>2</sup> ·°F), ASTM C 177		
	200°C (392°F)	0.023 (0.16)
	400°C (752°F)	0.026 (0.18)
	600°C (1112°F)	0.030 (0.21)
	800°C (1472°F)	0.036 (0.25)

### Shelf Life

- WDS NextraShell has unlimited shelf life if it stored properly
- WDS NextraShell must be handled and stored in dry conditions
- WDS NextraShell is resistant to diffusion by atmospheric humidity (water vapor) proving condensation is avoided

### Standard Dimensions and Availability

DN	Length, mm (in)	Thickness, mm (in)
DN15, DN20, DN25, DN32, DN40, DN50, DN65, DN80, DN100, DN125, DN200	500 (19.68)	20, 25, 30, 35, 40, 45, 50 (0.8, 1, 1.2, 1.4, 1.6, 1.8, 2)
Other diameters, lengths and thicknesses are available on demand		

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.