



# Kaowool® 1260 Paper

## Product Data Sheet

### Product Description

Kaowool 1260 Paper is manufactured from high-purity refractory fibres and designed for high-temperature insulation. Advanced production techniques ensure uniform fibre distribution and close control of thickness and density.

Kaowool 1260 Paper is produced from alumina-silicate fibres with the minimum addition of carefully selected bonds, which burn out cleanly in service.

Please contact your regional Morgan Advanced Materials - Thermal Ceramics representative to support your application requirements.

### Features

- Good resistance to tearing
- High flexibility
- Low shot content
- Precise thickness
- Resistant to thermal shock
- Very low thermal conductivity

### Applications

- Insulating thermal break
- Insulating gaskets
- Expansion joints
- Parting media
- Die-cut gaskets for domestic appliances
- Thermal barriers for vehicles (silencers, catalytic exhausts and heat shields)
- Fire protection

# Kaowool® 1260 Paper

## Product Data Sheet



Properties	Kaowool 1260 Paper	
Region of Manufacture	EMEA	
Color	white	
Classification Temperature, °C (°F), EN 1094-1 (2008)	1260 (2300)	
Continuous Use Temperature, °C (°F)	1176 (2150)	
Density, kg/m <sup>3</sup> (pcf), EN 1094-1 (2008)	200 (12.5)	
Tensile strength, MPa (psi), EN 1094-1 (2008)	0.51 - 0.68 (75 - 100)	
Loss of Ignition, %	6-10	
Chemical Analysis, %		
	Alumina, Al <sub>2</sub> O <sub>3</sub>	42-48
	Silica, SiO <sub>2</sub>	52-58
	Other	trace
Thermal Conductivity, W/m·K ( BTU·in/hr·ft <sup>2</sup> ·°F), ASTM C201		
	200°C (400°F)	0.06 (0.42)
	400°C (752°F)	0.09 (0.62)
	600°C (1112°F)	0.13 (0.90)
	800°C (1472°F)	0.2 (1.39)

### Product Availability

Kaowool 1260 Paper is manufactured in our EMEA region, and is available globally.

Please contact your regional Morgan Advanced Materials - Thermal Ceramics representative to support providing specific packaging availability for your local business needs.

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.