

#### SAFETY DATA SHEET

(Following Regulations (EC) No 1907/2006 & (EC) No 1272/2008)

SDS Number: PB1 Date of first issue: 01 October 1997 Date of last revision: 21 February 2022

#### 1 - Identification of product

#### 1.1 - Identification of Product

Tradenames: Morbond 170, Morbond 180, Morbond AL, Morgun AL,

The above-mentioned products are chemically bonded castables.

#### 1.2 - Use of Product

These products are monolithic refractories used in lining industrial furnaces, high temperature processing, kilns and metal melting applications

#### 1.3 - Identification of Company

U.K. THERMAL CERAMICS LIMITED

Tebay Road, Bromborough Wirral, Merseyside CH62 3PH Tel.: +44 (0) 151 334 4030 Fax: +44 (0) 151 334 1684

#### Website

www.morganthermalceramics.com sds.tc@morganplc.com

## 1.4 - Emergency information

Tel: + 44 (0) 7931 963 973

Language: English Opening hours: Only available during office hours

#### 2 - Hazard Identification

#### 2.1 - Classification of the substance/ mixture

# 2.1.1 CLASSIFICATION ACCORDING TO REGULATION (EC) NO 1272/2008

Not classified as hazardous according to Classification, Labelling and Packaging regulations (CLP) 1272/2008 EEC

# 2.2 - Labelling Elements

Not applicable

#### 2.3 - Other hazards which do not result in classification

Mild mechanical irritation to skin, eyes and upper respiratory system may result from exposure.

These effects are usually temporary.

When mixed with water, an increase in pH will occur. Alkaline mix may be irritating to skin and could cause damage to eyes.

## CHRONIC RESPIRATORY HEALTH EFFECTS

These products may contain minimal amounts of crystalline silica. Prolonged/repeated inhalation of respirable crystalline silica dust may cause delayed lung injury (silicosis). IARC (International Agency for Research on Cancer) states that there is "sufficient evidence in humans for the carcinogenicity of inhaled crystalline silica in the form of quartz or cristobalite from occupational sources to classify crystalline silica as carcinogenic to humans (Group 1)" (Monograph V 68). In making the overall evaluation the Working Group noted however that carcinogenicity in humans was not detected in all industrial circumstances studied.

# 3 - Composition / Information On Ingredients

These products are supplied as dry powders, which are added to a liquid phosphate to achieve set and required properties. MORGUN AL is added to water at a nozzle during gunning.

COMPONENT	% by weight	CAS No.		Hazard Classification according to CLP
Alumino Silicate	55-90	Not Applicable	Not yet available	Not classified as hazardous
Alumina	5-35	1344-28-1	01- 2119817795-27	Not classified as hazardous
Cement	< 10	65997-16-2	Not yet available	Not classified as hazardous
Other bonding product	< 5	13530-50-2	01- 2119490078-32	Not classified as hazardous

None of the components are radioactive under the terms of European Directive Euratom 96/29.

#### 4 - First-Aid measures

#### 4.1 - Description of First Aid Measures.

In case of skin irritation rinse affected areas with water and wash gently. Do not rub or scratch exposed skin.

#### Eyes

In case of eye contact flush abundantly with water; have eye bath available. Do not rub eyes. Seek medical attention is irritation persists.

#### **Nose and Throat**

If these become irritated move to a dust free area, drink water and blow nose. Seek medical attention if irritation persists.

If symptoms persist, seek medical advice.

## 4.2 - Most Important symptoms and effects, both acute and delayed

No symptoms or effects expected either acute or delayed

#### 4.3 - Indication of any immediate medical attention and special treatment required

No special treatment required, if exposure occurs wash exposed areas to avoid irritation.

## 5 - Fire-fighting measures

#### 5.1 - Extinguishing media

Use extinguishing agent suitable for surrounding combustible materials.

## 5.2 - Special hazards arising from the substance or mixture

Non-combustible products,

#### 5.3 - Advice for firefighters

Packaging and surrounding materials may be combustible.

#### 6 - Accidental Release Measures

## 6.1 - Personal precautions, protective equipment and emergency procedures

Provide the workers with appropriate protective equipment until the situation is restored to normal (see section 8).

#### 6.2 - Environmental precautions

Prevent further dust dispersion for example by damping the materials.

Do not flush spillage to drain and prevent from entering natural watercourses.

Check for local regulations, which may apply

#### 6.3 - Methods and materials for containment and clean up

Pick up large pieces and use a vacuum cleaner.

If brushes are used, ensure that the area is wetted down first. Do not use compressed air for clean up.

Do not allow to become windblown.

## 6.4 - Reference to other sections

For further information, please refer to sections 7 and 8

#### 7 - Handling and storage

#### 7.1 - Precautions for safe handling

Handling can be a source of dust emission and therefore the processes should be designed to limit the amount of handling. Whenever possible, handling should be carried out under controlled conditions (i.e., using dust exhaust system).

Regular good housekeeping will minimise secondary dust dispersal.

#### 7.2 - Conditions for safe storage

Store in original packaging in a dry area.

Avoid damaging the packaging.

Material supplied in multi-ply paper sacks or big bags.

# 7.3 - Specific end use

Please refer to your local Morgan Thermal Ceramics' supplier.

## 8 - Risk Management Measures / Exposures Controls / Personal Protection

#### 8.1 - Control parameters

Industrial hygiene standards and occupational exposure limits vary between countries and local jurisdictions. Check which exposure levels apply to your facility. If no regulatory dust or otherstandards apply, a qualified industrial hygienist can assist with a specific workplace evaluation including recommendations for respiratory protection. Examples of exposure limits for respirable dust (in November 2014) are given below:

COUNTRY	Total Dust (mg/m3)	Resp Dust (mg/m3)	Quartz (mg/m3)	Cristobalite (mg/m3)	Source
EU BOELV			0.1	0.1	Carcinogens and Mutagens Directive (Directive 2004/37/EC)
Belgium	10	3	0.1	0.05	Ministerie van Sociale Zaken en Werkgelegenheid
Denmark	10	5	0.10	0.05	Direktoratet fot Arbeidstilsynet
Finland	10	No limit	0.05	0.05	National Board of Labour Protection
France	10	5	0.10	0.05	Ministère du Travail
Germany	10	0.5^	0.05*	0.05*	Bundesministerium für Arbeit und Soziales
Italy	10	3	0.1	0.1	Decreto Legislativo 1 giugno 2020 n. 44
Netherlands	10	5	0.075	0.075	Ministerie van Sociale Zaken en Werkgelegenheid
Norway	10	5	0.10	0.05	Direktoratet for Arbeidstilsynet
Poland	10	No limit	0.1	0.1	Regulation of the Minister of Labour and Social
Romania		10	0.10	0.05	Government Decision regarding carcinogenic agents (in Annex 3: Quartz, Cristobalite, Tridymite).
Spain	10	3	0.05	0.05	Instrucciones de Técnicas Complementarias (ITC)
Sweden		5	0.10	0.05	National Board of Occupational Safety and Health
UK	10	4	0.10	0.10	Health & Safety Executive

<sup>^</sup> Defined for a density of 1 g/cm³, i.e. for minerals with a common density of 2,5 g/cm³, a calculated OEL of 1,25 mg/m³ applies.

## Information on monitoring procedures

United Kingdom

MDHS 14/4 - "General methods for sampling and gravimetric analysis of respirable, thoracic and inhalable aerosols" MDHS 101 - "Crystalline silica in respirable airborne dusts"

NIOSH

NIOSH 0500 "Particulates not otherwise regulated, total"

NIOSH 0600 "Particulates not otherwise regulated, respirable" NIOSH 7500 " Silica, Crystalline, by XRD (filter redeposition)"

#### 8.2 - Exposure controls

#### 8.2.1 APPROPRIATE ENGINEERING CONTROLS

Review your applications in order to identify potential sources of dust exposure.

Local exhaust ventilation, which collects dust at source, can be used. For example down draft tables, emission controlling tools and materials handling equipment.

Keep the workplace clean. Use a vacuum cleaner. Avoid brushing and compressed air.

If necessary, consult an industrial hygienist to design workplace controls and practices.

The use of products specially tailored to your application(s) will help to control dust. Some products can be delivered ready for use to avoid further cutting or machining. Some could be pretreated or packaged to minimise or avoid dust release during handling.

Consult your supplier for further details

# 8.2.2 - Personal Protective Equipment

Skin protection:

Use of gloves and work clothes is recommended.

Soiled clothes should be cleaned before being taken off (e.g. use vacuum cleaning, not compressed air).

Eye protection:

As necessary wear goggles or safety glasses with side shields.

For dust concentrations below the exposure limit value, RPE is not required but FFP2 respirators may be used on a voluntary basis.

For short-term operations where excursions are less than ten times the limit value use FFP2 respirators.

In case of higher concentrations or where the concentration is not known, please seek advice from your company and/or local Thermal Ceramics' supplier.

INFORMATION AND TRAINING OF WORKERS

Workers should be trained on good working practices and informed on applicable local regulations

#### 8.2.3 - Environmental Exposure Controls

Refer to local, national or European applicable environmental standards for release to air water and soil.

For waste, refer to section 13

<sup>\*</sup>Assessment Citerion (reference value)

## 9 - Physical and chemical properties

Information on basic physical and chemical properties

State Mix of grey aggregates and fine powders

Not applicable

Not applicable

Colour Not applicable

None

Odour

**Odour threshold** Not Applicable 6 - 10 Melting point/freezing point > 1650°C

Initial boiling point and boiling point range Not applicable Flash point Not applicable **Evaporation rate** Not Applicable Flammability (solid, gas) Not applicable

Upper/lower flammability or explosive limits Not applicable Vapour pressure Not applicable Vapour density Not Applicable Relative density > 2.10 T/m<sup>3</sup> Solubility(ies) Not applicable Partition co-efficient: n-octanol/water Not applicable

Auto-ignition temperature Not applicable **Decomposition temperature** Not Applicable Viscosity Not Applicable Not applicable **Particle Characteristics Explosive properties** Not applicable

10 - Stability and Reactivity

10.1 - Reactivity

The material is stable and non reactive.

10.2 - Chemical Stability

**Oxidising properties** 

The product is inorganic, stable and inert

10.3 - Possibility of Hazardous Reactions

None

10.4 - Conditions to Avoid

Careful heat up of the product is essential to avoid rapid loss of the chemical combined water during heat up (see section 16).

10.5 - Incompatible Materials

None

10.6 - Hazardous decomposition products

Upon heating above 900°C for sustained periods, this amorphous material begins to transform to mixtures of crystalline phases. For further information please refer to Section 16.

## 11 - Toxicological information

## Toxicokinetics, metabolism and distribution

# 11.1.1 BASIC TOXICOKINETICS

As manufactured, these products may contain a minimal amount of crystalline silica. Exposure is predominantly by inhalation or ingestion, available toxicological information is as follows:

# 11.1.2 Human Toxicological data

Epidemiology for crystalline silica Prolonged/repeated inhalation of respirable crystalline silica dust may cause delayed lung injury (silicosis).

In evaluating crystalline silica as a cancer risk, the International Agency for Research on Cancer (IARC) reviewed several studies from different industries and concluded that crystalline silica from occupational sources inhaled in the form of quartz or cristobalite is carcinogenic to humans (Group 1) [IARC Monograph; vol.68; June 1997]. However, in reaching its conclusion, IARC stated that the carcinogenicity in humans could not be found in all industries reviewed and that carcinogenicity might be dependent on inherent characteristics of crystalline silica or on external factors affecting biological activity (e.g., cigarette smoking) or distribution of its polymorphs.

# 11.1 - Information on hazard classes as defined in Regulation (EC) No 1272/2008

Experimental studies for crystalline silica

Animals exposed to very high concentrations of crystalline silica, artificially or by inhalation, have reported fibrosis and tumours (IARC Monographs 42 and 68).

Inhalation and intratracheal installation of crystalline silica in rats caused lung cancer. However, studies in other species such as mice and hamsters caused no lung cancer. Crystalline silica also caused fibrosis in rats and hamsters in several inhalation and intratracheal installation studies.

**ACUTE TOXICITY** 

Lethal dose 50 % (LD50) / lethal concentration 50% (LC50): N.A.

## 12 - Ecological information

#### 12.1 - Toxicity

These products are inert materials that remain stable overtime. No adverse effects of this material on the environment are anticipated.

#### 12.2 - Persistence and degradability

Not established

#### 12.3 - Bioaccumulative potential

Not established

#### 12.4 - Mobility in soil

No information available

#### 12.5 - Results of PBT and vPvB assessment

This mixture contains no substance considered to be persistent, bioaccumulating nor toxic (PBT).

This mixture contains no substance considered to be very persistent and very bioaccumulative (vPvB).

#### 12.6 - Endocrine Disrupting Properties

No additional information available

#### 12.7 - Other adverse effects

#### 13 - Disposal Considerations

Waste from these materials may be generally disposed off at a landfill, which has been licensed for this purpose. Please refer to the European list (Decision N° 2000/532/CE as modified) to identify your appropriate waste number, and insure national and/or regional regulations are complied with.

Unless wetted, such a waste is normally dusty and so should be properly sealed in containers for disposal. At some authorised disposal sites, dusty waste may be treated differently in order to ensure they are dealt with promptly to avoid them being windblown. Check for any national and/or regional regulations, which may apply.

#### 14 - Transport information

# 14.1. UN number

Not Applicable

## 14.2. UN proper shipping name

Not Applicable

#### 14.3. Transport hazard class(es)

Not Applicable

# 14.4. Packing group

Not Applicable

#### 14.5. Environmental hazards

Not Applicable

# 14.6. Special precautions for user

Not Applicable

#### 14.7. Transport in bulk according to Annex II of MARPOL73/78 and the IBC Code

Not Applicable

#### 15 - Regulatory information

## 15.1 - Safety health and environment regulations/legislation specific for the substances or mixtures

EU regulations:

- Regulation (EC) No 1907/2006 dated 18th December 2006 on Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH)
- Regulation (EC) No 1272/2008 dated 20th January 2009 on classification, labelling and packaging of substances and mixtures (OJ L 353)
- Annex of Regulation (EU) 2015/830
- Commission regulation (EC) No 790/2009 of 10 August 2009 amending, for the purposes of its adaptation to technical and scientific progress, Regulation (EC) No 1272/2008 of the European Parliament and of the Council on classification, labelling and packaging of substances and mixtures.
- The 1st Adaptation to Technical Progress (ATP) to Regulation (EC) No 1272/2008 enters into force on 25 September 2009.

# PROTECTION OF WORKERS

Shall be in accordance with several European Directives as amended and their implementations by the Member States:

- a) Council Directive 89/391/EEC dated 12 June 1989 "on the introduction of measures to encourage improvements in the safety and health of workers at work" (OJEC (Official Journal of the European Community) L 183 of 29 June 1989, p.1).
- b) Council Directive 98/24/EC dated 7 April 1998 "on the protection of workers from the risks related to chemical agents at work" (OJEC L 131 of 5 May 1998, p.11).

# OTHER POSSIBLE REGULATIONS

Member States are in charge of implementing European Directives into their own national regulation within a period of time normally given in the Directive. Member States may impose more stringent requirements. Please always refer to any national regulation.

## 15.2 - Chemical Safety Assessment

Chemical Safety Reports have been requested from suppliers, as soon as this information is available it will be shared with downstream users.

#### 16 - Other Information

- (the directives which are cited must be considered in their amended version)

   Council Directive 89/391/EEC dated 12 June 1989 "on the introduction of measures to encourage improvements in the safety and health of workers at work" (OJEC L 183 of 29 June 1989, p.1).

   Regulation (EC) No 1907/2006 dated 18th December 2006 on registration, Evaluation, Authorisation and Restriction of Chemicals (REACH)
- Regulation (EC) No 1272/2008 dated 20th January 2009 on classification, labelling and packaging of substances and mixtures (OJ L 353)
- Council Directive 98/24/EC of 7 April 1998 "on the protection of the health and safety of workers from the risks related to chemical agents at work" (OJEC L 131 of 5 May 1998, p11).

# RECOMMENDED HEATING PROCEDURE FOR MORGUN AL

The material may be heated after installation when it has set. Raise to 110-130°C and hold for 6 hours (<300 mm lining) or 24 hours (300-500 mm lining) or until steam ceases. Raise to 550-600°C at 25°C per hour and hold for 6-8 hours. Raise to working temperature at 50°C per hour (<300 mm lining) or 25°C (300-500 mm lining). For linings thicker than 500 mm or installations greater than 30 tons, contact Thermal Ceramics. This information is only a guide. Please refer, for each product, to the defined commissioning schedules provided by Thermal Ceramics.

RECOMMENDED HEATING PROCEDURE FOR THE OTHERS
Small (<100kg) precast shapes, provided they are not for immediate use in metal contact application, can be put directly into service after a short curing period. Curing period will be 2/3hours depending on the size of the component.

For larger components and in situ casting (<300mm lining) once set has occurred mouldings can be removed and the material air-dried until the exothermic reaction, which occurs on, setting has subsided. The temperature can be raised to 200-250°C and held for 4-6 hours and the further raised to 500-600°C at up to 50°C per hour and held for 6-8 hours. However, the length of hold will be dependent on backing materials used. For large and complex linings contact Morgan Thermal Ceramics. This information is only a guide. Please refer, for each product, to the defined commissioning schedules provided by Morgan Thermal Ceramics.

For more information connect to:

The Morgan Thermal Ceramics' website: (http://www.morganthermalceramics.com/)

Or ECFIA's website: (http://www.ecfia.eu)

#### **Revision Summary**

Update to Section 8

#### Technical data sheets

For more information on individual products please see the relevant technical data sheet available from http://www.morganthermalceramics.com/downloads/datasheets

#### NOTICE:

The information presented herein is based on data considered to be accurate as of the date of preparation of this Material Safety Data Sheet. However safe as provided by law, no warranty or representation, express or implied, is made as to the accuracy or completeness of the foregoing data and safety information, nor is any authorisation given or implied to practice any patented invention without a licence. In addition, no responsibility can be assumed by the vendor for any damage or injury resulting from abnormal use, from any failure to adhere to recommended practices, or from any hazards inherent in the nature of the product (however, this shall not act to restrict the vendor's potential liability for negligence or under statute).