



Superwool[®] Sealcoat HT

Product Data Sheet

Product Description

Superwool Sealcoat HT insulation is composed of Superwool HT, a low bio-persistent fiber, organic polymers, inorganic binders and other proprietary ingredients. This product is a pliable, low shrinkage, putty-like material that is supplied wet and premixed, ready for installation by a pneumatically applied system. The product is designed to seal furnace lining cracks and can be used as a hot face coating over fiber insulation and other refractory surfaces to restore and improve lining performance.

Installation Information

The HS-100 Extrusion pump is a piston extrusion pump which has been modified to pump Superwool Sealcoat HT in a fast, efficient manner. These modifications optimize the pump's capabilities to provide a complete delivery system. The Sealcoat Spray Nozzle assembly is designed to work in conjunction with the HS-100 Extrusion pump. The combined system allows for an efficient wet gunning technology. Sealcoat can also be applied by trowel or caulking gun.

Features

- Pliable, putty-like material composed of low biopersistent fibers, proprietary ingredients and inorganic binders
- Ready to use
- Resistant to thermal and mechanical breakdown
- Non-wetted in molten aluminum

Applications

- Grout refractory joints and gaps
- Hot face coating over fiber or dense refractory
- Seals furnace lining cracks
- Back-up lining
- Furnace maintenance and emergency repairs

Shelf Life

- Shelf life for Superwool Sealcoat HT is 24 months if stored correctly in a cool, non humid environment. Shelf life is calculated from date of manufacture noted on label.

Standard Dimensions and Availability

- Superwool Sealcoat HT is manufactured globally. Please reference contact your regional Morgan Advanced Materials - Thermal Ceramics representative for your local business needs.

	11oz caulking tube	32oz caulking tube	1 gallon pail	5 gallon pail
Superwool Sealcoat HT	X	X	X	X

Superwool[®] Sealcoat HT

Product Data Sheet



Properties		Superwool Sealcoat HT
Region of Manufacture		Europe
Colour		off-white
Continuous Use Temperature, °C		1538
Classification Temperature, °C		1593
Density, dried @110°C, kg/m ³		513-577
Density, wet, kg/m ³		1201
Solids, %		46
Aluminum Resistant cup test		
	816°C, 707.5 alloy, 72 hours	No penetration
Modulus of Rupture, dried, MPa		
	110°C	1.38
	1315°C	1.45
Compressive strength @10% deformation, MPa		
	dried	1,04
Compressive strength @10% deformation, fired, MPa, psi		
	1093°C	1.55
	1315°C	1.59
Permanent Linear Change, %, 24 hours		
	1093°C	-1.4
	1315°C	-1.4
	1426°C	-1.5
	1538°C	-1.6
Chemical Analysis, %		
	Silica, SiO ₂	86
	Calcium oxide, CaO	12
	Other	2

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.