

Product Description

An insulating castable based on insulating aggregate, for service up to 1320°C (2400°F), to be installed by gunning. It is recommended for applications requiring high mechanical strength and low lime content, such as working lining in radiant and convection zones in petrochemical heaters, kiln car tops, general high temperature applications where Sulphur is present in the fuel.

A separate casting version is available.

Properties	Firelite LW HS G
Region of Manufacture	Europe
Bond Type	Hydraulic
Method of application	Gun
Maximum Service Temperature, °C (°F)	1320 (2400)
ASTM C401-91 Classification	Q
Estimated weight of dry material/m ³ of construction, kg (lb)	1330 (83)
Water addition, % by weight	32
Maximum grain size, mm	6
Packaging in bags, kg (lb)	30 (66)

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

Firelite[®] LW HS G

Product Data Sheet



Density, kg/m ³ (pcf), ASTM C134	
oven dried, 110°C (230°F)	1430 (89.2)
after 5 hours firing, 815°C (1500°F)	1330 (83.0)
Cold crushing strength, MPa (psi), ASTM C133	
oven dried, 110°C (230°C)	14.7 (2131.5)
after 5 hours firing, 815°C (1500°F)	11.8 (1711)
Permanent linear change, %, ASTM C113	
after 5 hours firing, 815°C (1500°F)	-0.6
Thermal conductivity, W/m·K (BTU·in/hr·ft ² ·°F), ASTM C201/417	
200°C (392°F)	0.31 (2.15)
400°C (752°C)	0.33 (2.29)
600°C (1112°F)	0.36 (2.50)
800°C (1472°F)	0.38 (2.64)
1000°C (1832°F)	0.41 (2.84)
Chemical composition, %	
Alumina, Al ₂ O ₃	40.0
Silica, SiO ₂	36.2
Calcium Oxide, CaO	11.8
Ferric Oxide, Fe ₂ O ₃	6.8
Titanium Oxide, TiO ₂	1.1
Alkali as, MgO+K ₂ O+Na ₂ O	1.3
Loss of ignition	1.3

Storage and Shelf Life

- Should be stored in dry conditions, unopened packaging on pallets. Do not store on ground. Keep out of rain and damp conditions.
- Shelf life is of twelve months with original packaging, double shrink film and dehydrating agent provided if the monolithic is stored under these recommended conditions.

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.