

## Product Description

Kaolite 2500LI AHR is a low iron, lightweight monolithic with a special formulation to prevent alkali hydrolysis.

## Instructions for using

**Casting:** Highest strength is obtained with monolithic refractory by using the least amount of clean mixing water that will allow thorough working of material into place by vibration. A mechanical mixer is required for proper placement (paddle type mortar mixers are best suited). Mix for 3-6 minutes to achieve a good ball-in-hand consistency. Place material within 20 minutes after mixing.

**Precautions:** Watertight forms must be used when placing material. All porous surfaces that will come in contact with the material must be waterproofed with a suitable coating or membrane. For maximum strength, cure 24 hours under damp conditions before initial heat-up. Keep freshly placed monolithic warm during cold weather, ideally between 16°C and 27°C (60°F and 80°F) until wet curing is completed. New monolithic installation must be heated slowly the first time.

For detailed installation instructions and commissioning schedules, please contact your Morgan Advanced Materials-Thermal Ceramics representative.

Properties	Kaolite 2500LI AHR	
Region of Manufacture	Americas	
Bond type	Hydraulic	
Raw material base	Insulating Aggregate	
Method of installation	Cast	
Maximum grain size, mm	6	
Maximum service temperature, °C (°F)	1371 (2500)	
Net material requirement, kg/m <sup>3</sup> (pcf)	1185 (75)	
Water addition, % by weight		
	casting by vibrating	38-45
Packaging in bags, kg (lbs)	22 (50)	

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

# Kaolite<sup>®</sup> 2500LI AHR Monolithic

## Product Data Sheet



Properties		Kaolite 2500LI AHR
<b>Bulk Density, kg/m<sup>3</sup> (pcf), ASTM C134</b>		
	dried 24 hours @ 105°C (220°F)	1121-1298 (70-81)
	fired 5 hours @ 816°C (1500°F)	1008-1186 (63-74)
<b>Modulus of Rupture, MPa (psi), ASTM C133</b>		
	dried 24 hours @ 105°C (220°F)	1.38-2.00 (200-290)
	fired 5 hours @ 816°C (1500°F)	0.86-1.72 (125-250)
	fired 5 hours @ maximum service temperature °C (°F)	2.07-4.14 (300-600)
<b>Cold Crushing Strength, MPa (psi), ASTM C133</b>		
	dried 24 hours @ 105°C (220°F)	4.14-8.27 (600-1200)
	fired 5 hours @ 816°C (1500°F)	4.14-7.59 (600-1100)
	fired 5 hours @ maximum service temperature °C (°F)	5.17-8.97 (750-1300)
<b>Permanent Linear Change, %, ASTM C113</b>		
	dried 24 hours @ 105°C (220°F)	0 to -0.2
	fired 5 hours @ 816°C (1500°F)	-0.1 to -0.6
	fired 5 hours @ maximum service temperature °C (°F)	-0.2 to -1.2
<b>Chemical Analysis, %, Calcined Basis</b>		
	Alumina, Al <sub>2</sub> O <sub>3</sub>	47
	Silica, SiO <sub>2</sub>	40
	Ferric Oxide, Fe <sub>2</sub> O <sub>3</sub>	0.8
	Titanium Oxide, TiO <sub>2</sub>	1.2
	Calcium Oxide, CaO	11 (5)
	Magnesium Oxide, MgO	0.2
	Alkali as, K <sub>2</sub> O+Na <sub>2</sub> O	1
<b>Thermal Conductivity, W.m•K (BTU•in/hr•ft<sup>2</sup>•°F) , ASTM C417</b>		
	260°C (500°F)	0.27 (1.90)
	538°C (1000°F)	0.30 (2.05)
	816°C (1500°F)	0.32 (2.23)
	1093°C (2000°F)	0.35 (2.43)
Chemical Analysis % for CaO in parentheses indicates the % of reactive CaO present if less than the total. The balance is Calcia from the anorthite aggregate.		

### Storage and Shelf Life

- Monolithics should be stored in a dry, well-ventilated area and held off the ground on pallets ideally with the original packaging intact. Keep out of rain and damp conditions.
- Normal shelf life is 9 months from date of manufacture when properly stored.

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.